

Attn: Mr Ken Grace m/s EC. GROUP
4-9 Delaine Ave Edwardstown S A 5069

LABORATORY TEST REPORT
P172354

Sample description as provided by customer Pile weight mass/unit area **35** oz/yd² Construction Details **Tufted** Secondary Backing **Synthetic** Style **Multi Level Loop** 

Order No. KG
Pile Fibre Content 100% SOLUTION DYED NYLON
Colour Grey/White
Pile Height mm

149

TEST METHOD: AS.ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the Building Code of Australia (BCA) and National Construction Code 2015 (NCC) specifications C1.10. Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date Aug 2017

Test Date 18 Sep 2017

Total Thickness

mm

135

## Assembly System: DIRECT STICK (Details Below).

The floor covering was directly stuck to the substrate using Roberts 95 adhesive.

**Substrate: Non-Combustible** - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring. The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests:

(%.min)

Smoke Development Rate

**Length** Direction Critical Radiant Flux **4.8** kW/m<sup>2</sup> **Width** Direction Critical Radiant Flux **4.6** kW/m<sup>2</sup>

Specimen Tests conducted in the Width Direction

Specimen #1 Specimen #2 Specimen #3 Mean

Critical Radiant Flux (kW/m²) 4.6 4.9 4.9 4.8

121

The values quoted below are as required by BCA and NCC Specification C1.10 Fire Hazard Properties (Floors). The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

134

## Mean Critical Radiant Flux 4.8 kW/m<sup>2</sup>

## Mean Smoke Development Rate 135 %.min

Observations: The samples shrunk away from the heat source, ignited and burnt a relatively short distance.

AS.ISO 9239.1 Clause 9(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCA and NCC is given on this test report page.

Page 1 of 2

(v5-0, 11/03/2017)

