

Sample description as provided by customer  
 Pile weight mass/unit area 35 oz/yd<sup>2</sup>  
 Construction Details Tufted Secondary Backing Synthetic  
 Style Loop Pile

Order No. K  
 Pile Fibre Content 100% SOLUTION DYED NYLON  
 Colour Cream/Grey  
 Pile Height mm

TEST METHOD: AS.ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the Building Code of Australia (BCA) and National Construction Code 2015 (NCC) specifications C1.10. Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date Nov 2017 Test Date 01 Dec 2017 Total Thickness mm

## Assembly System: OVER UNDERLAY AIRSTEP STEPEZY

The UNDERLAY used was AIRSTEP STEPEZY.

Substrate: Non-Combustible - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.  
 The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests: Length Direction Critical Radiant Flux 2.4 kW/m<sup>2</sup>  
 Width Direction Critical Radiant Flux 2.0 kW/m<sup>2</sup>

Specimen Tests conducted in the Width Direction				
	Specimen #1	Specimen #2	Specimen #3	Mean
Critical Radiant Flux (kW/m <sup>2</sup> )	2.0	2.2	2.4	2.2
Smoke Development Rate (%.min)	196	200	206	201

The values quoted below are as required by BCA and NCC Specification C1.10 Fire Hazard Properties (Floors).  
 The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).


**Mean Critical Radiant Flux 2.2 kW/m<sup>2</sup>**

**Mean Smoke Development Rate 201 %.min**

Observations: The samples shrunk away from the heat source, ignited and burnt a relatively short distance.

AS.ISO 9239.1 Clause 9(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCA and NCC is given on this test report page.



**M. B. Webb**  
 Technical Manager

DATE: 01 Dec 2017

ACCREDITED FOR TECHNICAL COMPETENCE

Performance & Approvals  
 Accreditation No. 15393  
 Accredited for compliance with ISO/IEC 17025.

